

High Temperature Chocking Compound

Technical Bulletin # 666G

Product Description

CHOCKFAST® Black is a specifically formulated 100% solids, inert filled casting compound developed for use as a chocking material. It is a cost-effective method of maintaining permanent precise alignment of critical equipment. It will withstand severe environments involving high physical and thermal shock.

Use & Benefits

This unique product is used under gas and diesel engines, compressors, generators, turbines, motors, pumps and various other types of equipment. CHOCKFAST® Black is ideal for use under these hot running reciprocating and rotating machines because of its excellent resistance to creep and fatigue at high operating temperatures. It is non-shrinking and has a very high impact and compressive strength. Resin chocks made with CHOCKFAST® Black reduce possible bearing or crankshaft damage because they (1) minimize heat build-up on foundations, (2) assure precise and unsurpassed contact with bedplates, and (3) provide a high coefficient of friction to help hold engines down tight. The excellent flowability of CHOCKFAST® Black allows it to fill voids in the chock area and conform to all surface irregularities


Design Considerations

CHOCKFAST® Black was designed to be a thick pour liquid chocking material. A chock depth of 2" (50mm) is standard; however, thinner or thicker pours can be made satisfactorily. The 2" (50mm) chock elevates equipment above the underlying foundation, which allows a free flow of air thereby reducing possible foundation humping problems.

Contact ITW Polymer Technologies for information regarding pours less than 1-1/4" (32mm) in thickness or greater than 2-1/2" (62mm) in thickness.

Installation Instructions

Construct a chock mold around one or more anchor bolts using open cell foam damming material on three sides. Wrap the shank of the anchor bolt with tape, cover with foam pipe insulation or coat with non-melt grease to prevent the CHOCKFAST from sticking to it and to seal the bolt hole. Place a metal dam 1/2" to 3/4" (12mm to 18mm) from the mounting pad and seal with caulk. Spray the inside of the mold and front metal dam with Release Agent. Mix and pour the epoxy as directed.

**ITW POLYMER TECHNOLOGIES**

130 Commerce Drive • Montgomeryville, PA 18936 • 215-855-8450 • Fax 215-855-4688
www.chockfast.com



ITW Polymer Technologies
Registered to ISO 9001:2009
File No. A3790



ITW Performance Polymers Europe
ISO 9001:2009
Q 05-120

Physical Properties

COMPRESSIVE STRENGTH	17,300 psi (1,216 kg/cm ²)	ASTM C-695 (Modified)
COMPRESSIVE MODULUS OF ELASTICITY	800,000 psi (56,000 kg/cm ²)	ASTM C-695 (Modified)
LINEAR SHRINKAGE	0.00018 in/in (0.00018 mm/mm)	ASTM D-2566
COEFFICIENT OF LINEAR THERMAL EXPANSION	32°F to 140°F @ 15.0 X 10 ⁻⁶ /F° (0.000027/C° @ 0°C to 60°C)	ASTM D-696
FLEXURAL STRENGTH	6,200 psi (435 kg/cm ²)	ASTM C-580
FLEXURAL MODULUS OF ELASTICITY	1,400,000 psi (101,300 kg/cm ²)	ASTM C-580
TENSILE STRENGTH	2,900 psi (204 kg/cm ²)	ASTM D-638
SHEAR STRENGTH	5,000 psi (350 kg/cm ²)	FED-STD-406 (Method 1041)
IZOD IMPACT STRENGTH	5.1 in.lbs./in (0.23 N.m/cm)	ASTM D-256
FIRE RESISTANCE	Self Extinguishing	ASTM D-635
SPECIFIC GRAVITY	1.94	
BARCOL HARDNESS	55 Full Cure	ASTM D-2583
MAXIMUM OPERATING TEMPERATURE	200°F (94°C)	

Product Information

UNIT COVERAGE	265 in ³ (4,343 cm ³)
APPLICATION TEMPERATURE	55°F (13°C) to 95°F (35°C)
UNIT PACKAGING	Resin (NH) – 18.2 lbs. (8.3 kg), 1.2 gal (4.5 L) in a 2gal pail Hardener (H) – 0.74 lbs. (0.34 kg), 11.5 oz (3.4 L) in an 16 oz plastic bottle
SHIPPING WEIGHT	21 lbs. (9.5 kg)
CURE TIME (approximate)	48 hours @ 60°F (15°C) 36 hours @ 65°F (18°C) 24 hours @ 70°F (21°C) 18 hours @ 80°F (26°C)
POT LIFE	45 min. @ 70°F (21°C)
SHELF LIFE	Exceed 18 months
CLEAN UP	IMPAX IXT-59 or similar epoxy cleaner

Reference

For design considerations and application details please request Bulletin No. 642 or contact ITW Polymer Technologies' Engineering Services Department.

Date

06/2006

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support.

Warranty: ITW Polymer Technologies, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment.

Warranty Claims: If any product fails to meet the above, ITW Polymer Technologies will, at its option, either replace the product or refund the purchase price. ITW Polymer Technologies will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered.

Disclaimer: ITW Polymer Technologies makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose.

Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Polymer Technologies' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Polymer Technologies' election. Under no circumstances shall ITW Polymer Technologies be liable for any indirect, incidental or consequential damages.

Modification of Warranty: No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Polymer Technologies. No term of any purchase order shall serve to modify any provision of this document.

Mediation and Arbitration: If any dispute arises relating to products or product warranties, either the purchaser or ITW Polymer Technologies may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.